

MULTI-PURPOSE JOINT COMPOUND
Updated Feb'20


Multi-purpose Joint Compound is specially formulated as ready to use skim coat material to smoothen uneven plastering wall, painted surfaces and gypsum to give a smooth and excellent finishing.

Product Features

- Good workability
- Good sanding property
- Ideal for patching cracks and drywall joints
- Good compatibility and adhesion with wide range Nippon paint interior paints
- For interior wall surface and ceiling
- Long lasting

| Paint Type | Product Type | Finishing | Recommended Substrate | Pack Size |
|-------------|--------------|------------------|--|-------------|
| Water based | Interior | Smooth finishing | Masonry, brick, plastering substrate and fibre board | 5 kg, 28 kg |

Composition

| | |
|---------|---|
| Pigment | : Mainly Mineral Extender |
| Binder | : Vinyl acetate ethylene, polyvinyl alcohol |
| Thinner | : Water |

Technical Data

| | | |
|----------------------|--|--|
| Drying Time | : Touch Dry | : 30 minutes (Dependent on temperature and humidity) |
| | : Hard Dry | : 1 hour (Dependent on temperature and humidity) |
| Recoating Time | : 2 hours (Dependent on temperature and humidity) | |
| Dry Film Thickness | : Around 100 µm per coat (based on substrate condition) | |
| No. of Coats | : 2 coats | |
| Theoretical Coverage | : 4 – 5 m ² per kg per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance) | |
| Solid Content | : ~ 73% | |
| Shelf Life | : Up to 36 months in tight sealed container | |

Application Method

| | |
|--------|--|
| Trowel | : Apply by trowel. No dilution required. |
|--------|--|

Recommended Coating System

| | | |
|-----------------|--|-----------|
| Basecoat | : Multi-purpose Joint Compound | : 1 Coat |
| Sealer / Primer | : Acrylic 5170 Wall Sealer / Hi-Bond Wall Sealer | : 1 Coat |
| Top Coat | : Nippon Interior Products | : 2 Coats |

Surface Preparation

Remove all loose, defective paint or powdery residues, loose chalk, dust and foreign matter. Repair cracks, uneven surfaces with Multi-purpose Joint Compound or suitable fillers. Smoothen the putty / filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with Nippon Interior Wall Sealer.

Cleaning

Clean up equipment with water immediately after use.

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.