

NIPPON PAINT ETCHING PRIMER 120
Updated Aug'22

NIPPON PAINT ETCHING PRIMER 120 is a two-pack polyvinyl butyral based, acid-catalysed etching primer. It has excellent adhesion to blast cleaned steel, galvanized steel and light alloys and thus provides a suitable base for most coatings to adhere satisfactorily.

Product Features:

- Good adhesion

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Solvent based	Interior & Exterior	Matt Olive Green	Blast cleaned steel, galvanized steel and light alloys	5 L (4L Base and 1L Hardener)

Composition

Pigment	: Anti rust and Extender
Binder	: Polyvinyl butyral based resin
Thinner	: Mixture of hydrocarbon solvents

Technical Data

Drying Time (25-30°C)	: Touch Dry : Approximately 5 minutes (Dependent on temperature and humidity)
	: Hard Dry : 1 hour (Dependent on temperature and humidity)
Overcoating Time (25-30°C)	: Minimum 4 hours (Dependent on temperature and humidity)
Typical Thickness	: 12 µm dry film per coat 60 µm wet film per coat
No. of Coats	: 1 coat
Theoretical Coverage	: 16.7 m ² /litre (for dry film thickness of 12 microns)
Practical Coverage (40% Loss Factor, as a guideline)	: 10.0 m ² /litre (for dry film thickness of 12 microns)
Volume Solid	: 20 ± 2% by volume
Specific Gravity	: 0.85 - 1.00 (for mixture of Base and Hardener)
Mixing Ratio	: 4 parts by volume of Base to 1 part by volume of Hardener. <i>(Stir the content of the Base component, continue stirring and gradually add the total contents of the Hardener component, continue stirring until a homogeneous mix is obtained.)</i>
Pot Life (25-30°C)	: 18 - 24 hours after mixing
Shelf Life	: Up to 24 months in tight sealed container (Subjected to reinspection after exceeding shelf-life period)

Application Method

Thinner	: Vinilex 510 Thinner
Brush/ Roller	: If necessary, add about 5% thinner by volume.
Compressed Air Spray	: If necessary, add about 10% to 15% thinner by volume.
Airless Spray	: Delivery pressure : 140 – 170 kg/cm ² : Tip size : 0.015" – 0.017" : Spray angle : 60° - 70° : Dilution : Up to 5% thinner by volume

Recommended Coating System

Iron and Steel		
Primer	: Nippon Paint Etching Primer 120	: 1 Coat
Intermediate	: Nippon Paint Protective Finish FD	: 1 Coat
Top Coat	: Nippon Paint Protective Finish FD	: 1 Coat

Primer	: Nippon Paint Etching Primer 120	: 1 Coat
Intermediate	: Nippon Paint Micaceous Iron Oxide	: 1 Coat
Top Coat	: Nippon Paint Protective Finish FD	: 1 Coat
Primer	: Nippon Paint Etching Primer 120	: 1 Coat
Intermediate	: Nippon Paint Micaceous Iron Oxide	: 1 Coat
Top Coat	: Nippon Paint Micaceous Iron Oxide	: 1 Coat
Primer	: Nippon Paint Etching Primer 120	: 1 Coat
Intermediate	: Nippon Paint 8048	: 1 Coat
Top Coat	: Nippon Paint Polyurethane Recoatable Finish	: 1 Coat
Primer	: Nippon Paint Etching Primer 120	: 1 Coat
Top Coat	: Nippon Paint Polyurethane Recoatable Finish	: 1- 2 Coat

Surface Preparation

For galvanised surfaces and light alloys, thorough solvent degreasing to **SSPC-SP1** is necessary. For steel, abrasive blast **Sa 2½ ISO 8501-1:2007** is required. All surfaces must be dry and free from dirt, grease, oil and other contaminants before application of the paint.

Cleaning

Cleaning Solvent : Vinilex 510 thinner. Clean up equipment with thinner immediately after use.

Environmental Conditions During Application

- Do not apply when the relative humidity exceeds 85% or when the surface to be coated is less than 3°C above the dew point.
- Do not apply at temperature below 7°C. If not, drying and overcoating times will be considerably extended.
- During application of the paint, naked flame, welding operations and smoking should not be allowed and good ventilation is necessary.

Safety Precautions

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- During application of paint, naked flames, welding operation, and smoking should not be allowed.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula and does not consider Loss Factor.

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness } (\mu)} \right] = \text{m}^2/\text{lit}/\text{coat}$$

This theoretical coverage rate has been calculated from the volume solids of the material and is related to the amount of coating applied onto a perfectly smooth surface without wastage. For a practical coverage rate, due allowance should be made for atmospheric conditions, surface roughness, geometry of the article being coated, the skill of applicator, method of application etc. when estimating quantities required for a particular job.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.
We reserve the right to alter the given without prior notice.