



PUR GLASS COATING

Product Description:

PUR Glass Coating is a two-pack high grade and high gloss polyurethane paint suitable for interior and exterior use on properly cleaned glass surface. PUR Glass Coating provides great performance properties, such as excellent flow and levelling, film hardness and exterior durability.

Recommended Uses:

Ideal for use on PUR Solid colour paint as glass coating.

Properties:

PUR Glass Coating

***Drying Time at 25°C – 30°C**

Touch Dry : 1 hours
Handle Dry (light pressure) : Minimum 8 hours

Pot Life : 5 hours at 25°C.

Curing Time at 25°C – 30°C : Fully cured after 5-6 days

Theoretical Coverage : 9 m²/litre
(For dry film thickness of 35 microns. This is calculated value. The actual loss factor may vary depending on the application condition, method and technique.)

*These conditions do not mean that paint has reached full curing. It is a stage where handling can be achieved without loosening, wrinkling or otherwise marring the paint under minimal pressure from fingers or hands. Drying time may vary, depending on film build, color selection, temperature, humidity and degree of air movement.

Application Parameters:

PUR Glass Coating Solid Paint

The parameters given below are general guidelines for spraying. These may have to be adjusted to suit environmental conditions.

Application Method	:	By Compressed Air Spray Spray 2-4 coats. Flash-off for 2 - 4 minutes between coats.
Spray Viscosity	:	16-18 seconds/F#4/Cup
Dilution	:	20% PUR thinner.
Spray Pressure	:	4.0 – 4.5 kg/cm ²
Recommended Thinner	:	PUR Thinner
Recommended Hardener	:	Glass Coating Hardener
Mixing Ratio (by volume)	:	PUR Glass Coating Solid : 4 parts Glass Coating Hardener : 1 part

Surface Preparation:

All surfaces must be clean and dry..

Safety, Health and Environmental Information:

Keep container tightly closed and keep out of reach of children or away from food and drink. Ensure good ventilation during application and drying. When applying paint, it is advisable to wear eye protection and aspirator. In case of contact with eye, rinse with plenty of water immediately and seek medical advice. Paint must always be stored in a cool place. When transporting paint, care must be taken. Always keep container in a secure upright position. Dispose of any paint waste in accordance with the appropriate Environmental Quality Regulations.

Note:

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given data without notice.

Standard Packing	:	1 Litre of Base with 250ml of Hardener 4 Litre of Base with 1L of Hardener
-------------------------	---	---