### **MOMENTO SPARKLE**

Updated Oct'24



Momento Sparkle let's you recreate intricate works of Italian craftsmanship in your home with its distinctive special effects that turn ordinary walls into extraordinary masterpieces. Momento Sparkle is formulated with low VOC, contains no lead or mercury and formaldehyde-free.

### Product Features:

- Adds a dash of glitz to walls for a finish that sparkles like a gem
- Hides unevenness of the wall surface
- Low odour, environmental friendly

| Paint Type           | Product<br>Type  | Finishing  | Recommended Substrate               | Pack Size             |  |
|----------------------|--|--|-------------------------------------|-----------------------|--|
| Water based          | Interior   | Texture  | Walls, ceiling, cement-based        | 1 Litre & 5 Litres    |  |
|                      |  | Sparkle (Gold /  | plaster, gypsum-based plaster,      |                       |  |
|                      |  | Silver / Pearl)  | brickwork, hard and soft boards     |                       |  |
|                      |  |  | and asbestos                        |                       |  |
| Composition          |  |  |                                     |                       |  |
| Pigment              | : Organic pig  | : Organic pigments, Mineral Extender and Special Effect Pigments   |                                     |                       |  |
| Binder               | : Acrylic Poly   | : Acrylic Polymer Dispersion   |                                     |                       |  |
| Thinner              | : Water  | : Water  |                                     |                       |  |
| Technical Data       |  |  |                                     |                       |  |
| Drying Time          | : Touch Dry  |  |                                     |                       |  |
|                      | : Hard Dry : 2 – 4 hours (Dependent on temperature and humidity) |  |                                     |                       |  |
| Recoating Time       | : 4 hours  |  |                                     |                       |  |
| Dry Film Thickness   | : 100 µm pe  | : 100 $\mu$ m per coat (Actual thickness per coat is based on texture required and painter   |                                     |                       |  |
|                      | application)   |  |                                     |                       |  |
| No. of Coats         | : 1 – 2 coats  |  |                                     |                       |  |
| Theoretical Coverage | method, a  | <ul> <li>: 6 – 8 m<sup>2</sup> per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance)</li> <li>It is recommended to go for actual application to estimate the practical coverage for project.</li> </ul> |                                     |                       |  |
| Volume Solid         | : Not applicable   |  |                                     |                       |  |
| Shelf Life           | : Up to 12 months in tight sealed container                      |  |                                     |                       |  |
| Application Meth     | od   |  |                                     |                       |  |
| Brush / Roller       |  | ooth Scrapper (to  | create design)                      |                       |  |
| Recommended Co       | oating System  |  |                                     |                       |  |
| Sealer               |  | : 5200 Interior Sealer / Hi-Bond Wall Sealer (on powdery or skim-coated : 1 Coat surface)  |                                     |                       |  |
| Primer               | ,  | : Momento Primer : 2 Coats   |                                     |                       |  |
| Finishing Coat       |  | : Momento Sparkle : 1 – 2 Coats  |                                     |                       |  |
| Clear Coat           |  | : Momento Clear Coat : 1 – 2 Coats   |                                     |                       |  |
| Surface Preparati    | on   |  |                                     |                       |  |
|                      |  | wdory rosiduos k   | oose chalk, dust and foreign matter | Ronair cracks, unovon |  |

surfaces with EasySKIM 5000 All Purpose Joint Compound or suitable fillers. Smoothen the putty / filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of

# D NIPPON PAINT<sup>®</sup>

## **TECHNICAL DATA SHEET**

the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with Nippon Interior Wall Sealer.

### Cleaning

Clean up equipment with water immediately after use.

### **Safety Precautions**

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

#### Note

\* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{Volume \ Solid \ \% \ x \ 10}{Dry \ Film \ Thickness}\right] = m^2/lit/coat$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.